

(18)



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

**0 186 917
B1**

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication of patent specification: 25.01.89

(21) Application number: 85201634.4

(22) Date of filing: 09.10.85

(51) Int. Cl.⁴: **C 08 L 69/00, C 08 L 67/02 //**
(C08L69/00, 67:02,
51:00),(C08L67/02, 69:00,
51:00)

(54) Polymer mixture with polycarbonate and/or polyester.

(30) Priority: 31.10.84 NL 8403295

(43) Date of publication of application:
09.07.86 Bulletin 86/28

(45) Publication of the grant of the patent:
25.01.89 Bulletin 89/04

(84) Designated Contracting States:
DE FR GB IT NL

(56) References cited:

EP-A-0 025 920
EP-A-0 036 127
EP-A-0 050 265
EP-A-0 064 648
DE-A-3 202 477
DE-A-3 245 467
NL-A-7 316 732
NL-A-7 706 327
US-A-3 808 180

(73) Proprietor: **GENERAL ELECTRIC COMPANY**
1 River Road
Schenectady New York 12305 (US)

(72) Inventor: **Lohmeijer, Johannes Hubertus
Gabriel M.**
General Electric Plastics B.V. P.O. Box 117
NL-4600 AC Bergen op Zoom (NL)
Inventor: **Heuschen, Jean Marie Hubert**
General Electric Plastics B.V. P.O. Box 117
NL-4600 AC Bergen op Zoom (NL)

(74) Representative: **Schüler, Horst, Dr. et al**
Kaiserstrasse 69
D-6000 Frankfurt/Main 1 (DE)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European patent convention).

Courier Press, Leamington Spa, England.

EP 0 186 917 B1

Description

The invention relates to a polymer mixture which comprises the following constituents:

(a) 30—70% by weight of aromatic polycarbonate;

(b) 20—60% by weight of aromatic polyester;

(c) 5—15% by weight of a polymer having an elastomeric core from at least 50% w. of one or more alkyl acrylates or aralkyl acrylates, a cross-linking agent, and a graft linking agent and a rigid thermoplastic shell.

Polymer mixtures which may comprise an aromatic polycarbonate, an aromatic polyester and a polymer with a rubber-like first phase and a rigid thermoplastic final phase, are described in WO 80/00972. The known mixtures have a good impact strength and a good tensile strength, in particular in comparison with a pure aromatic polyester. It has furthermore been found in practice that these known polymer mixtures have a good resistance to organic solvents, for example, motor spirit. The known polymer mixtures exhibit two small disadvantages: articles obtained by injection moulding show the tendency to a phenomenon which may be referred to as nacrous lustre. This means that these articles sometimes have a surface showing nacrous lustre. A second disadvantage is the occurrence of a discoloring of the surface (turning white) after contact with organic solvents, for example, motor spirit. For applications in which high requirements are imposed as regards the appearance of the formed articles, these two disadvantages make it necessary to provide the articles with a protective layer of lacquer.

The invention provides a new polymer mixture having the same good mechanical properties as the known polymer mixtures without the above-mentioned disadvantages occurring. The invention is based on the discovery that by a proper choice of the particle size of the polymer (c) the said disadvantages do not occur.

The polymer mixture according to the invention is characterized in that the polymer (c) has a volume average particle size of less than 0.2 micrometres. Particle size is always to be understood to mean the size as determined according to the method to be described hereinafter, in so far as at least not otherwise stated.

The invention also relates to polymer mixtures which comprise

a) 85—99.5% by weight of aromatic polycarbonate and

b) 0.5—15% by weight of a polymer (c) as meant above having a volume average particle size of less than 0.2 micrometres.

The invention furthermore relates to polymer mixtures which comprise

a) 85—99.5% by weight of aromatic polyester and

b) 0.5—15%, by preference 10—15%, by weight of a polymer (c) as meant above having a volume average particle size of less than 0.2 micrometres.

The invention provides in particular polymer mixtures which comprise a polymer (c) as described in US—A—3,808,180. The polymers described therein consist of a multiphase composite interpolymer having a first phase with a glass temperature of less than 10°C. This first phase has been obtained by polymerisation of at least 50% by weight of one or more alkyl and aralkyl acrylates, approximately 0.05 to 5.0% by weight of a cross-linking monomer, approximately 0.05 to 5.0% by weight of a graft-linking monomer, approximately 0 to 10% by weight of a hydrophilic monomer and the remainder of further copolymerisable ethenically unsaturated monomers. As a cross-linking monomer is used a polyethenically unsaturated monomer having several groups which are reactive for addition polymerisation and which all react at approximately the same rate. The graft-linking monomer is a polyethenically unsaturated monomer having several groups which are reactive for addition polymerisation and at least one of which polymerises at a reaction rate which differs considerably from the reaction rate of at least one of the remaining reactive groups. The polymer (c) according to US 3,808,180 furthermore comprises a final phase of a rigid thermoplastic material which is polymerised in the presence of the elastomeric phase mentioned hereinbefore from a monomer mixture consisting for at least for 50% by weight of an alkyl methacrylate. Between the elastomeric phase and the final phase an intermediate phase may be present, for example, an intermediate phase of styrene.

The polymer (c) as used in the polymer mixtures according to the invention may comprise in the elastomeric phase, for example, an n-butyl acrylate or a 2-ethylhexylacrylate. 2-Ethylhexylacrylate is to be preferred. When 2-ethylhexylacrylate is used in the elastomeric phase, a polymer (c) is obtained which, when used in the polymer mixtures according to the invention, leads to a polymer mixture having a particularly good resistance to petrol (substantially no discoloring). As a cross-linking monomer may be used polyacrylates or polymethacrylates of polyoles, for example butylene diacrylate. In the preparation of polymer (c) a graft-linking monomer is also used. Suitable graft-linking monomers are, for example, allylmethacrylate and allylacrylate. The elastomeric phase may comprise further copolymerisable monomers in addition to the above-mentioned alkylacrylate and/or aralkylacrylate and the said monomers. The rigid final phase may be built up from a C₁—C₄ alkylmethacrylate, for example, methylmethacrylate or also from a copolymer of styrene and acrylonitrile.

The preparation of polymer (c) is known per se. It is also known how a polymer (c) of a given particle size can be obtained. For this purpose, reference may be made to the above-mentioned US—A—3,808,180 and to the article by J. Vandegaer in J. Appl. Pol. Sc. 9, 2929 (1965).

EP 0 186 917 B1

The known polymer (c) may be mixed according to US 3,808,180 with rigid polymers, for example, acryl polymers. The "particle size of the elastomer" according to US 3,808,180 is "not of any essential significance".

5 The way in which the particle size is determined and which size is meant (diameter or radius) or the way in which the size is calculated (average according to number or to volume) has not been indicated in the prior art.

Assignee of US 3,808,180 markets a product under the indication Acryloid® KM 330 which falls within the scope of the said Patent Specification (for this purpose see, for example, EP—A—36 127 and implicitly WO 80/00972).

10 When the particle size of this product (Acryloid® KM 330) is determined by means of a scanning electron microscope in the manner described hereinafter, a particle size of 0.46 micrometres is found.

The polymer (c) as described in US—A—3,808,180 has already been used in the form of polymer mixtures with a poly(alkyleneterephthalate) (see US—A—4,096,202), with a poly(carbonate) (EP—A—0.036.127), with a poly(alkyleneterephthalate) plus a poly(carbonate) (WO 80/00972 and EP—A—0,025,920).

15 The particle size of the polymer (c) used is not indicated anywhere; usually it is stated that the commercial product Acryloid® KM 330 is used as a polymer (c).

The found relationship between the particle size and the occurrence of nacrous lustre and the occurrence of white spots after contact with organic solvents could not be predicted. The association between these factors is not known either for similar polymers.

20

Determination particle size

In so far as not stated otherwise in this Application and in the Claims, particle size of polymer (c) is always to be understood to mean the dimension determined as follows. In preparing polymer (c) a latex is obtained from which polymer (c) is recovered. For the determination of the particle size this latex is used as the starting material. This latex is centrifuged in a highly diluted form by means of an analytic centrifuge (type CAPA® 500 of Horiba, Japan). The size of the sedimenting particles is determined according to the method described by W. Scholtan, Kolloid Zeitschrift 250, 782—96, (1972)). Always determined is the volume-averaged particle size, namely the average particle diameter as the D₅₀ number.

25 This method was not suitable for determining the particle size of the commercially available product Acryloid® KM 330, because the particles showed some form of agglomeration. Therefore, the particle size has also been determined in articles formed from the polymer mixture according to the invention and in articles formed from a polymer mixture which comprises the commercial product Acryloid® KM 330. Polymer mixtures having 8.5 parts by weight of polymer (c), 40 parts by weight of polybutylene terephthalate, 50 parts by weight of bisphenol-A-polycarbonate, 0.5 part by weight of titanium dioxide, 0.05 part by weight of carbon black and stabilizers were mixed in an extruder at 265°C. The extrudate was granulated. The granulate was injection moulded. The resulting articles were fractured at -196°C. The particles of polymer (c) were made visible in the fracture surface by means of a scanning electron microscope. The average diameter of 100 particles is indicated below as the "s.e.m. value". Generally a smaller value for the diameter is found with this method as compared with the above-described method.

40 A polymer (c) having a particle size of less than 0.2 micrometres can be prepared according to known methods. A suitable method of preparation is indicated (1st polymer c).

The invention is based on the discovery that polymer mixtures which comprise an aromatic polycarbonate, an aromatic polyester, and a polymer (c) having a particle size of less than 0.2 micrometres, have no nacrous lustre and show no white spots when in contact with organic solvents. Polymer mixtures comprising an aromatic polycarbonate and a polymer (c) having a particle size smaller than 0.2 micrometres, and polymer mixtures comprising an aromatic polyester and a polymer (c) having a particle size of smaller than 0.2 micrometres will show a similar improvement of properties as compared with similar polymer mixtures comprising the known Acryloid® KM 330 having a particle size of 0.46 micrometres (s.e.m. value).

50 In the polymer mixture according to the invention a polymer (c) is preferably used having a comparatively high degree of cross-linking corresponding to a degree of swelling of less than 7 g per gram (determined in the manner described hereinafter).

The commercially available polymer (c) (KM 330) has a degree of swelling of 5 g per gram. Application of a polymer (c) having a degree of swelling of less than 7 g per gram leads to a polymer mixture having a reduced nacrous lustre (for the same particle size).

55 The polymer mixture according to the invention comprises, in addition to the polymer (c), an aromatic polycarbonate and an aromatic polyester.

Aromatic polycarbonates are compounds known per se. Suitable aromatic polycarbonates are described, for example, in US—A—4,034,016. Particularly suitable are the polycarbonates comprising units derived from bisphenol A and/or tetramethyl bisphenol A. It is also possible to use so-called branched polycarbonates.

60 Aromatic polyesters are compounds also known per se. The so-called polyalkylene terephthalates, for example, polyethylene terephthalate and polybutylene terephthalate, are particularly suitable. The aromatic polyesters are prepared by reaction of one or more aromatic dicarboxylic acids, for example terephthalic acid, esters or ester-forming derivatives thereof, with one or more different diol compounds. Suitable diol

65

EP 0 186 917 B1

compounds are ethylene glycol, 1,4-butanediol and 1,6-hexane diol. A part of the aromatic dicarboxylic acid may be replaced by an aliphatic dicarboxylic acid. Mixtures of one or more polyesters are also suitable.

The polymer mixtures according to the invention can be obtained according to the usual method of preparing polymer mixtures. The polymer mixtures according to the invention are conventionally prepared by mixing the constituents a), b), and c) in an extruder and extruding them. The extrudate is then granulated.

The polymer mixtures according to the invention can be formed into articles by means of the shaping techniques for thermoplastic materials, in particular by injection moulding.

The polymer mixtures may furthermore comprise the conventional additives, for example, fillers, for example, in the form of reinforcing fibres, stabilizers, dyes, flame-retarding agents, softeners, mould-detaching agents, seed-forming agents, and the like.

The preparation of 1st polymer (c)

1.0. Polymer (c) having a particle size of smaller than 0.2 micrometres.

1.1. The following solutions were prepared:

A. 506.9 parts by weight of n-butylacrylate
2.6 parts by weight of allylmethacrylate
2.6 parts by weight of tris(2-acryloxy-ethyl) isocyanurate (FA 731 A van Hitachi)

B. 6.4 parts by weight of sodium (n-dodecyl benzene sulphonate)
530 parts by weight of demineralized water

C. 1.6 parts by weight of $K_2S_2O_8$ (potassium peroxydisulphate)
120 parts by weight of demineralized water

D. 1.6 parts by weight of $Na_2S_2O_5$ (sodium disulphite)
120 parts by weight of demineralized water

A glass two litre reactor was filled with A and B, cooled to 10°C and made oxygen-free by rinsing/evacuating five times with nitrogen. The mixture of A and B was emulsified by stirring. The temperature was then raised to 40°C. 60 Parts by weight of solution C (deaerated) were then injected, succeeded by 60 parts by weight of solution D (deaerated). The polymerisation reaction started immediately, which resulted in a rise in temperature to 70—75°C in 10 minutes: the temperature was then adjusted at 60°C and the pressure at 1.5 atmospheres. The remainders of solutions C and D (deaerated) were gradually added in a period of 2 hours by means of dosing pumps. Stirring for another hour at 60°C was then carried out to complete the reaction.

1.2. The following solutions were prepared and deaerated:

E. 127.4 parts by weight of methylmethacrylate
0.6 parts by weight of allylmethacrylate

F. 1.6 parts by weight of sodium (n-dodecyl benzene sulphonate)
0.4 parts by weight of $K_2S_2O_8$ (potassium peroxydisulphate)
100 parts by weight of demineralized water

G. 0.4 parts by weight of $Na_2S_2O_5$ (sodium disulphate)
100 parts by weight of demineralized water

The solutions E, F and G were gradually added to the reaction mixture obtained sub 1.1 while stirring over a period of 1 hour. The reaction was then continued for 30 minutes at 85°C. The particle size of the latex thus obtained was determined as indicated above.

1.3. The resulting latex was destabilized by pouring the contents of the reactor through a filter into a rapidly stirred aqueous solution with 1% by weight of $CaCl_2$. The precipitated polymer (c) was isolated by filtration, washed with water, and dried in a vacuum at 60°C.

The particle size was 0.17 micrometer.

2nd. Polymer (c) having a particle size of more than 0.2 micrometre (0.32 micrometre).

A two-litre glass reactor was filled, while stirring with 500 parts by weight of water, after which 160 parts by weight of a latex prepared as indicated sub 1.1. were added. The reactor with contents was made oxygen-free by rinsing/evacuating five times with nitrogen. The assembly was heated to a temperature of 60°C under a pressure of 1.5 atmospheres. Deaerated solutions A to D as described sub 1.1. were gradually added in a period of three hours. The temperature rose to 62—63°C. Finally, stirring was carried out for

EP 0 186 917 B1

another 90 minutes at 60°C.

- 2.2. As indicated sub 1.2.
- 2.3. As indicated sub 1.3.

5

3rd. Polymer (c) having a particle size of more than 0.2 micrometres (0.61 micrometres).

3.1. The method described sub 2.1. was repeated, the starting-material, however, being an initial batch of 400 parts by weight of water and 30 parts by weight of latex obtained according to 1.1.

- 10 3.2. As indicated sub 1.2.
- 3.3. As indicated sub 1.3.

4th, 5th, 6th Polymer (c)

15 The methods as described for the 1st, 2nd and 3rd, polymer (c), respectively, were repeated, a solution A being used, however, consisting of 499.2 parts by weight of n-butyl acrylate, 2.56 parts by weight of allyl methacrylate and 10.24 parts by weight of tris (2-acrylyloxy-ethyl) isocyanurate.

7th, 8th, 9th Polymer (c)

20 The methods as described for the 1st, 2nd and 3rd polymer (c), respectively, were repeated, a solution A being used, however, consisting of 488.96 parts by weight of n-butylacrylate, 2.56 parts by weight of allylmethacrylate, and 20.48 parts by weight of tris(2-acrylyloxy-ethyl) isocyanurate.

25 Of the resulting polymers (c) 1 to 9, the average particle diameter (D_{v50}) was determined, as well as the degree of swelling and the gel content (gel fraction). For determining the degree of swelling and the gel fraction, a given quantity of polymer (c) was weighed (A). This quantity was suspended in toluene at room temperature in a concentration of 1.5% by weight and kept in suspension for 4 hours. The suspension was then centrifuged (28000 G), the supernatant clear liquid was decanted, the resulting gel was mixed with fresh toluene and again centrifuged. The supernatant clear liquid was again decanted. The weight of the remaining gel was determined (B). The remaining gel was then dried to constant weight (C). The degree of swelling (ZG) is the ratio between B and C; the gel fraction (GF) is calculated from

$$\frac{C}{A} \times 100\%$$

35

The results obtained are recorded in Table A hereinafter.

Table A

40

	Polymer (c) no.	Average particle size D_{v50} (micrometres)	ZG (g/g)	GF (wt.%)
45	1	0.17	11.7	94.3
50	2	0.32	9.5	95.5
	3	0.61	8.8	95.1
	4	0.18	7.9	96.2
55	5	0.34	6.5	95.2
	6	0.57	5.5	95.0
	7	0.16	5.7	94.9
	8	0.30	5.4	96.6
60	9	0.52	5.2	96.1

65 The polymers (c) Nos. 1, 4 and 7 are suitable for the polymer mixtures according to the invention; the polymers (c) Nos. 2, 3, 5, 6, 8, and 9 have been used for comparative examples.

EP 0 186 917 B1

Example I

8.5 Parts by weight of always one of the polymers (c) 1 to 9 were mixed in an extruder at 265°C with 40 parts by weight of polybutylene terephthalate (melting index according to ISO 1133 at 250°C, 50 N = 24 g per 10 minutes), 50 parts by weight of polycarbonate derived from bisphenol A (melting index according to ISO 1133 at 300°C, 12 N = 11 g per 10 minutes), 0.5 parts by weight of titanium dioxide, 0.05 parts by weight of carbon black and stabilizers. The extrudate was granulated. The granulate was formed into test bars by injection moulding. Two further polymer mixtures were also prepared: one without polymer (c) and one with 8.5 parts by weight of the commercially available Acryloid® KM 330.

The melting index (MFI) according to ISO 1133 was determined of the resulting granulates as well as of the starting polymers. The notch impact strength at -15°C was determined according to ASTM D 256 (bar thickness 3.2 mm). The discoloring (turning white) of the surface and nacrour lustre effects were determined in plates having a dimension of 6 × 6 cm.

The turning white was measured as follows. The plates were immersed for 6 minutes in a mixture of 85% by volume of "Fuel C" (according to ISO 1817) and 15% by volume of methanol. The plates were then dried in air for 24 hours. The discoloring was measured with a Zeiss RFC 3 spectrophotometer and calculated according to DIN 6174. The turning white is quantified by the ΔL^*_{ab} contribution expressed in so-called Cielab units. A low absolute ΔL^*_{ab} value indicates a small extent of turning white, a high ΔL^*_{ab} value a high extent of turning white. The nacrour lustre effects are evaluated visually by inspecting the plates at different angles and under different light sources and paying attention to changes in colour. When no changes in colour occurred (i.e. no nacrour lustre), an evaluation was given; strong change in colour is evaluated by numeral 1.

The particle size of polymer (c) in the polymer mixture is determined in the manner as described hereinbefore by means of a scanning electron microscope.

The results are recorded in Table B hereinafter.

Table B

Polymer mixture with polymer (c) No.	s.e.m. particle size (micrometres)	Melting index (g/10 minutes)	Notch impact strength at -15°C (J/m)	ΔL^*_{ab} (Cielab- units)	Nacrous lustre
1	0.13	13.0	740	4.1	4
2	0.28	13.0	686	10.0	3
3	0.37	11.2	683	13.5	1
4	0.13	13.7	613	5.1	4
5	0.30	13.0	590	9.5	3
6	0.37	12.9	542	11.9	2
7	0.12	13.7	573	6.8	5
8	0.26	12.9	525	9.1	4
9	0.38	11.0	480	10.1	3
None	-	16.8	100	0.2	5
Acryloid® KM 330	0.46	13.3	580	12.7	1

EP 0 186 917 B1

It may be seen from Table B that the polymer mixtures comprising the polymers (c) Nos. 1, 4, and 7 show the most favourable combination of little turning white and no or little nacrous lustre effects. Comparison of the polymer composition comprising polymer (c) No. 7 with the compositions containing polymer (c) No. 4 and No. 1 shows that polymer (c) No. 7 leads to a smaller nacrous lustre effect. The most important difference between polymers (c) Nos. 1, 4, and 7 is the degree of swelling (see Table A); polymer (c) No. 7 has the lowest degree of swelling. On the basis of this result, a polymer (c) is to be preferred having a low degree of swelling of less than 7 g per g. The effect of the degree of swelling on the nacrous lustre appears even more significant when the polymer mixtures with a polymer (c) Nos. 9, 6, and 4 are compared mutually. The use of polymer (c) with the lowest degree of swelling leads to the best evaluation for the nacrous lustre.

Example II

In a manner comparable to that described hereinbefore for the 4th polymer (c), a polymer (c) was prepared in which 2-ethylhexylacrylate was used instead of n-butylacrylate.

The average particle size (s.e.m. diameter value) of this polymer (c) in the fracture surface of a polymer mixture according to the invention (prepared as described in Example I with the above-meant polymer (c) based on ethylhexylacrylate) was 0.14 micrometres. The melting index of the polymer mixture was 14.0 g/min. The notch impact strength at -15°C : 6.5 J/m. The nacrous lustre was evaluated by the numeral 4 and the ΔL^*_{ab} value was only 0.5 Cielab units.

Example III

A polymer (c) was prepared in a manner similar to that described in Example II (i.e. elastomeric phase from 2-ethylhexylacrylate), in which the last phase was not copolymerized from methylmethacrylate but from a mixture of styrene and acrylonitrile (weight ratio respectively 71:29).

The average particle size (s.e.m. diameter value) of the resulting polymer (c) in a polymer mixture according to Example I with this polymer (c) was 0.12 micrometre. The polymer mixture had a melting index of 16 g per 10 minutes, a notch impact strength at -15°C of 580 J/m, a nacrous lustre value 4 and a ΔL^*_{ab} value of 1.0 Cielab unit.

Example IV

A second portion of polymer (c) no. 7 as referred to on pages 12 and 13 hereabove was prepared. The average particle size was 0.17 micrometres, the degree of swelling 5.9 g/g and the gelfraction 95.0% by weight.

8.5 Parts by weight of the above-mentioned polymer (c) were admixed with 90.95 parts by weight of the same polycarbonate as mentioned hereabove (page 14, line 1), 0.5 parts by weight of titanium dioxide, 0.05 parts by weight of carbon black and stabilizers.

As comparison a similar blend was prepared by using 8.5 parts by weight of the commercially available Acryloid® KM 330 instead of the polymer (c) no. 7.

By testing the obtained materials the following results have been obtained (Table C).

Table C

Polymer mixture with polymer (c)	Melting index (g/10 minutes)	Notched impact strength at -15°C (J/m)	ΔL^*_{ab} (Cielab units)	Nacrous lustre
no. 7	7.0	681	8.4	4
Acryloid® KM 330	6.7	650	23.2	3

As can be seen from the above Table C the blend according to the invention with polymer (c) no. 7 shows superior L values and has a smaller nacrous lustre.

Claims

1. A polymer mixture which comprises the following constituents:
 - (a) 30—70% by weight of aromatic polycarbonate;
 - (b) 20—60% by weight of aromatic polyester;
 - (c) 5—15% by weight of a polymer having an elastomeric core from at least 50% w. of one or more alkyl acrylates or aralkyl acrylates, a cross-linking agent and a graft linking agent and a rigid thermoplastic shell, characterized in that the polymer (c) has a volume average particle size of less than 0.2 micrometres.
2. A polymer mixture as claimed in Claim 1, characterized in that the polymer (c) has a degree of swelling of less than 7 g/g.
3. A polymer mixture as claimed in Claim 1, comprising
 - (a) 40—60% by weight of aromatic polycarbonate;
 - (b) 30—50% by weight of aromatic polyester;
 - (c) 8—12% by weight of the polymer (c).
4. A polymer mixture as claimed in Claim 1, characterized in that the polymer (c) has an elastomeric core which comprises ethylhexylacrylate.
5. A polymer mixture which comprises
 - (a) 85—99.5% by weight of aromatic polycarbonate, and
 - (b) 0.5—15% by weight of a polymer (c) as claimed in Claim 1.
6. A polymer mixture which comprises
 - (a) 85—99.5% by weight of aromatic polyester and
 - (b) 0.5—15%, by preference 10—15%, by weight of a polymer (c) as claimed in Claim 1.

Patentansprüche

1. Polymermischung, die die folgenden Bestandteile enthält
 - (a) 30 bis 70 Gew.-% aromatisches Polycarbonat,
 - (b) 20 bis 60 Gew.-% aromatischen Polyester,
 - (c) 5 bis 15 Gew.-% eines Polymeren mit einem elastomeren Kern aus wenigstens 50 Gew.-% eines oder mehrerer Alkylacrylate oder Aralkylacrylate, eines Vernetzungsmittels und eines gepfropft-gebundenen Mittels und eines starren thermoplastischen Mantels, dadurch gekennzeichnet, daß das Polymer (c) eine durchschnittliche Volumenteilchengröße von weniger als 0,2 Mikrometer aufweist.
2. Polymermischung nach Anspruch 1, dadurch gekennzeichnet, daß das Polymere (c) einen Quellungsgrad von weniger als 7 g/g aufweist.
3. Polymermischung nach Anspruch 1, enthaltend
 - (a) 40 bis 60 Gew.-% aromatisches Polycarbonat,
 - (b) 30 bis 50 Gew.-% eines aromatischen Polyesters,
 - (c) 8 bis 12 Gew.-% des Polymeren (c).
4. Polymermischung nach Anspruch 1, dadurch gekennzeichnet, daß das Polymere (c) einen elastomeren Kern aufweist, der Äthylhexylacrylat umfaßt.
5. Polymermischung, die enthält:
 - (a) 85 bis 99,5 Gew.-% aromatisches Polycarbonat und
 - (b) 0,5 bis 15 Gew.-% eines Polymeren, das
 - (c) die in Anspruch 1) enthaltene Bedeutung aufweist.
6. Polymermischung, die enthält:
 - (a) 85 bis 99,5 Gew.-% eines aromatischen Polyesters und
 - (b) 0,5 bis 15%, vorzugsweise 10 bis 15 Gew.-% eines Polymeren (c), wie es in Anspruch 1) beansprucht ist.

Revendications

1. Mélange de polymères qui comprend les constituants suivants:
 - (a) de 30 à 70% en poids de polycarbonate aromatique;
 - (b) de 20 à 60% en poids de polyester aromatique;
 - (c) de 5 à 15% en poids d'un polymère ayant un noyau élastomérique constitué pour au moins 50% en poids par un ou plusieurs acrylates d'alkyles ou acrylates d'aralkyles, un agent de réticulation et un agent de greffage et une enveloppe thermoplastique rigide, caractérisé en ce que le polymère (c) présente une dimension particulaire moyenne en volume de moins de 0,2 micromètre.
2. Mélange de polymères selon la revendication 1, caractérisé en ce que le polymère (c) présente un degré de gonflement de moins de 7 g/g.
3. Mélange de polymères selon la revendication 1, comprenant:
 - (a) de 40 à 60% en poids de polycarbonate aromatique;
 - (b) de 30 à 50% en poids de polyester aromatique;
 - (c) de 8 à 12% en poids du polymère (c).

EP 0 186 917 B1

4. Mélange de polymères selon la revendication 1, caractérisé en ce que le polymère (c) a un noyau élastomérique qui comprend de l'acrylate d'éthylhexyle.

5. Mélange de polymères qui comprend

- 5 (a) de 85 à 99,5% en poids de polycarbonate aromatique et
(b) de 0,5 à 15% en poids d'un polymère (c) selon la revendication 1.

6. Mélange de polymères qui comprend:

- (a) de 85 à 99,5% en poids de polyester aromatique et
(b) de 0,5 à 15% et, de préférence, de 10 à 15% en poids d'un polymère (c) selon la revendication 1.

10

15

20

25

30

35

40

45

50

55

60

65